

Material data sheet

SWG 2343 (EX3)

material characteristics	material number / grade	SWG 2343 (SWG EX3)					
	DIN standard	X37CrMoV5-1					
	comparable grade	AISI H11					
	chemical composition - reference analysis [%]	C	Si	Mn	Cr	Mo	V
		0.36	1.00	0.35	5.00	1.20	0.40
	production technology	EAF/LF/VD, forging, EFS annealing					
	service hardness / strength	HB	HRC	N/mm ²			
		-	36 - 52	-			
	delivery condition	annealed	≤ 229	-	-		
	maximum dimension	diameter		thickness			
≤ 800 mm		≤ 600 mm					
US-specification	EN 10228-3		SEP 1921				
	table 3 - type 1 - qual. class 3		group 3 - class D,d				
cleanliness	DIN 50602		ASTM E45 method A				
	K4 ≤ 20		A ≤ 1,5; B, C, D ≤ 2				
					variation upon request		

technological properties		0	1	2	3	4	5	comment	
	toughness		■	■					in relation to service hardness 42 - 48 HRC
	hot strength at working temp.		■	■	■	■			
	wear resistance		■	■	■	■			
	corrosion resistance	■							
	machinability		■	■	■	■			annealed
	polishability		■	■					ISO/SPI:N2/A-2 48-52HRC; higher: 2343 ESR
	weldability		■						CET = 0.77 % acc. DIN EN 1011-2
	texturability		■	■					for texturing 2343 ESR
	nitridability		■	■	■	■	■		nitriding hardness 900 - 1200 HV1
chrome-platability		■	■					for chrome plating 2343 ESR	

rating properties: 0 = not suitable; 1 = low; 2 = middle; 3 = good; 4 = very good; 5 = perfectly suitable

physical properties	thermal conductivity [W · m ⁻¹ · K ⁻¹]	20 °C	200 °C	300 °C	500 °C
		23.6	28.2	28.4	27.4
	coefficient of thermal expansion between 20 °C and ... [10 ⁻⁶ · K ⁻¹]	100 °C	200 °C	300 °C	500 °C
		11.8	12.4	12.6	12.8
elastic modulus [kN/mm ²]	20 °C	200 °C	300 °C	500 °C	
	212	199	192	175	


application	technology	mold making, injection molding, die-casting, gravity casting, drop forging
	tools	extrusion tools, forging dies, hot shear blades, mandrels, mold inserts, die-casting molds, prototyping molds
	process temperature	300 - 600 °C
	tool size	small- and medium-sized tools
	final products	light metal, steel forgings, strip steel, sheets and tubes, plastic parts (with glass fibre)
	features	-

SWG processing instructions	welding, texturing, vacuum hardening
-----------------------------	--------------------------------------


heat treatment		T min [°C]	T max [°C]	medium / comment
	annealing	820	840	furnace until 650 °C, air
	hardening	990	1010	vacuum, oil
	tempering	530	650	air, protective gas
	stress relieving	500	550	min. 30 °C below tempering temp.
	pre-heating before welding	300	320	
	nitriding	480	550	min. 30 °C below tempering temp.
	PVD-treating	480	550	

diagrams/ structure	CCT-diagram	yes
	tempering diagram	yes
	advice on heat treatment	vacuum hardening after pre-machining
	microstructure	martensitic

Tempering diagram: Average values on samples dia 25 mm x length 50 mm; hardened at 1020 °C in oil



CCT-diagram



PLEASE NOTE: The information contained in this data sheet is unbinding. It merely serves the first orientation of the user. Therefore, we do not assume any liability for the correctness, completeness or up-to-dateness of such data. In case of an order, the properties of the product are exclusively subject to the provisions of the respective contract.

© Schmiedewerke Gröditz GmbH, Gröditz